

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization International Bureau



(43) International Publication Date
20 October 2005 (20.10.2005)

PCT

(10) International Publication Number
WO 2005/097313 A1

(51) International Patent Classification⁷: B01J 20/26, A61F 13/15, 13/49, 13/53, B01J 20/30

(74) Agent: MATSUMOTO, Takehiko; 25-6, Hannan-cho 1-chome, Abeno-ku, Osaka-shi, Osaka, 5450021 (JP).

(21) International Application Number: PCT/JP2005/004858

(22) International Filing Date: 11 March 2005 (11.03.2005)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data: 2004-105117 31 March 2004 (31.03.2004) JP

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SM, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IS, IT, LT, LU, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

— with international search report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.



WO 2005/097313 A1

(54) Title: AN AQUEOUS-LIQUID-ABSORBING AGENT AND ITS PRODUCTION PROCESS

(57) **Abstract:** An aqueous-liquid-absorbing agent according to this invention is the one comprising water-absorbent resin particles as essential components, wherein the particles are obtained by a process including the step of polymerizing a water-soluble ethylenically unsaturated monomer and have a crosslinked structure in their inside; with the agent exhibiting FSR of not less than 0.2 g/g/s, CRC of 5 to 25 g/g, SFC of not less than 400 x 10⁻⁷m³•s/g, and a wet porosity of not less than 20 %. A process according to this invention for obtaining such an agent is characterized by comprising the steps of: obtaining a hydrogel from an aqueous monomer solution including a water-soluble ethylenically unsaturated monomer and an internal-crosslinking agent of not less than 0.2 mol % in ratio to the monomer; and then extruding this hydrogel from a perforated structure having perforation diameters in the range of 0.3 to 6.4 mm to thereby pulverize the hydrogel.